

VICTREX FG™ 200 Series



Product Description

High performance Food Grade thermoplastic material, unreinforced, glass fiber and carbon fiber reinforced PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection moulding and extrusion, colour natural/beige and black.

Regulatory

Food Contact compliance for EU 10/2011 (FG200 & FG220), FDA 21CFR 177.2415 (FG200, FG220, & FG240), China (FG200 & FG220) and South America (FG200 & FG220).

Drinking water compliance to WRAS (UK).

Typical Application Areas

The VICTREX FG™ 200 family of materials is intended for applications needing TOUGHNESS: ductility from sub-ambient to elevated temperatures along with long-term fatigue resistance and low coefficient of thermal expansion for metal replacement. Chemically resistant to aggressive environments, suitable for sterilisation for food contact applications.

| MATERIAL PROPERTIES | | | | | | |
|----------------------------------|---------------------|-------------|-----------------------------------|----------|----------|----------|
| | CONDITIONS | TEST METHOD | UNITS | FG200 | FG220 | FG240 |
| Mechanical Data | | | | | | |
| Tensile Fatigue | 23°C, 1E06 cycles | | MPa | 80 @2Hz | 100 @5Hz | 175 @5Hz |
| | 120°C, 1E06 cycles | | MPa | | 75 @5Hz | 120 @5Hz |
| Izod Impact Strength | Notched, 23°C | ISO 180/A | kJ m ⁻² | 9.5 | 8.0 | 10.5 |
| | Unnotched, 23°C | ISO 180/U | | No break | 55 | 50 |
| Tensile Strength | @yield, 23°C | ISO 527 | MPa | 95 | | |
| | @break, 23°C | | | | 185 | 265 |
| Tensile Elongation | @break, 23°C | ISO 527 | % | 60 | 2.8 | 1.7 |
| Flexural Strength | @3.5% yield, 23°C | ISO 178 | MPa | 120 | | |
| | @break, 23°C | | | 155 | 275 | 380 |
| | 125°C | | | 85 | 190 | 275 |
| | 175°C | | | | 80 | 130 |
| | 275°C | | | | 50 | 65 |
| Flexural Modulus | 23°C | ISO 178 | GPa | 3.6 | 11 | 24 |
| Compressive Strength | 23°C | ISO 604 | MPa | 120 | 250 | 320 |
| | 120°C | | | 65 | 160 | 200 |
| | 200°C | | | | 55 | 70 |
| Thermal Data | | | | | | |
| Melting Point | | ISO 11357 | °C | 343 | 343 | 343 |
| Glass Transition (Tg) | Onset | ISO 11357 | °C | 143 | 143 | 143 |
| | Midpoint | | | 150 | 150 | 150 |
| Coefficient of Thermal Expansion | Along flow below Tg | ISO 11359 | ppm K ⁻¹ | 45 | 18 | 5 |
| | Average below Tg | | | 65 | 45 | 40 |
| | Along flow above Tg | | | 125 | 18 | 6 |
| | Average above Tg | | | 160 | 110 | 100 |
| Heat Deflection Temperature | 1.8 MPa | ISO 75A-f | °C | 152 | 328 | 334 |
| Thermal Conductivity | Average, 23°C | ISO 22007-4 | W m ⁻¹ K ⁻¹ | 0.29 | 0.30 | 0.95 |
| Miscellaneous | | | | | | |
| Density | Crystalline | ISO 1183 | g cm ⁻³ | 1.30 | 1.51 | 1.40 |
| Shore D hardness | 23°C | ISO 868 | | 84 | 87.5 | 87.5 |
| Water Absorption by immersion | Saturation, 23°C | ISO 62-1 | % | 0.45 | 0.3 | 0.3 |
| | Saturation, 100°C | | | 0.55 | 0.45 | 0.45 |

| Electrical Properties | | | | | | |
|-----------------------|---------------|-------------|---------------------|------------------|------------------|------------------|
| Volume Resistivity | 23°C | IEC 60093 | Ω cm | 10 ¹⁶ | 10 ¹⁶ | 10 ^{5*} |
| Dielectric Strength | 2mm thickness | IEC 60243-1 | kV mm ⁻¹ | 23 | 25 | - |

*This property provided for informational purposes only – resistivity is not controlled

| Typical Processing | | | |
|---------------------------|---|---|---|
| Conditions | FG200 | FG220 | FG240 |
| Drying Temperature / Time | 150°C / 3h or 120°C / 5h (residual moisture <0.02%) | | |
| Temperature settings | 375 / 380 / 385 / 390 / 395°C (Nozzle) | 360 / 370 / 375 / 380 / 385°C (Nozzle) | 375 / 380 / 385 / 390 / 395°C (Nozzle) |
| Hopper Temperature | Not greater than 100°C | | |
| Mould Temperature | 170°C - 200°C (max 250°C) | 180°C - 200°C (max 250°C) | 180°C - 210°C (max 250°C) |
| Runner | Die / nozzle >3mm, manifold >3.5mm | | |
| Gate | >1mm or 0.5 x part thickness | >2mm or 0.5 x part thickness | |

| Mould Shrinkage + Spiral Flow | | | | | | |
|-------------------------------|-------------------|-----------|-------|-------|-------|-------|
| Conditions | | Method | Units | FG200 | FG220 | FG240 |
| Nozzle Temperature | | | °C | 395 | 385 | 395 |
| Tool temperature | | | °C | 180 | 190 | 200 |
| Spiral Flow | 1mm thick section | Victrex | mm | 125 | 85 | 75 |
| | 3mm thick section | | % | 630 | 410 | 330 |
| Mould Shrinkage | Along flow | ISO 294-4 | % | 0.9 | 0.3 | 0.1 |
| | Across flow | | | 1.3 | 0.9 | 0.5 |

Important notes:

- Processing conditions quoted in our datasheets are typical of those used in our processing laboratories
 - Data for mould shrinkage should be used for material comparison. Actual mould shrinkage values are highly dependent on part geometry, mould configuration, and processing conditions.
 - Mould shrinkage differs for along flow and across flow directions. "Along flow" direction is taken as the direction the molten material is travelling when it exits the gate and enters the mould.
 - Mould shrinkage is expressed as a percent change in dimension of a specimen in relation to mould dimensions.
- Data are generated in accordance with prevailing national, international and internal standards, and should be used for material comparison. Actual property values are highly dependent on part geometry, mould configuration and processing conditions. Properties may also differ for along flow and across flow directions.

Victrex plc and/or its group companies ("Victrex plc") believes that the information contained in this document is an accurate description of the typical characteristics and/or uses of the product or products, but it is the customer's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy, and safety for each end-use product, device or other application. Suggestions of uses should not be taken as inducements to infringe any particular patent. The information and data contained herein are based on information we believe reliable. Mention of a product in this document is not a guarantee of availability. Victrex plc reserves the right to modify products, specifications and/or packaging as part of a continuous program of product development. Victrex plc makes no warranties, express or implied, including, without limitation, a warranty of fitness for a particular purpose or of intellectual property non-infringement, including, but not limited to patent non-infringement, which are expressly disclaimed, whether express or implied, in fact or by law. Further, Victrex plc makes no warranty to your customers or agents, and has not authorized anyone to make any representation or warranty other than as provided above. Victrex plc shall in no event be liable for any general, indirect, special, consequential, punitive, incidental or similar damages, including without limitation, damages for harm to business, lost profits or lost savings, even if Victrex has been advised of the possibility of such damages regardless of the form of action. VICTREX™, APTIV™, VICOTE™, VICTREX PIPES™, VICTREX HT™, VICTREX ST™, VICTREX WG™, PEEK-ESD™ and the Triangle (Device), are trademarks of Victrex plc or its group companies.

