

### Technical Data Sheet



## SustaPEEK MG black

PEEK

#### Typical characteristics

- High purity
- Good sterilisation resistance
- High Strength
- High rigidity
- High-temperature stable up to 250°C in continuous operation
- ISO 10993-5 tested on semi-finished product
- Chemical resistant

#### Typical industries

- Healthcare

|   | Test method                 | Unit                 | Guideline value |
|---|-----------------------------|----------------------|-----------------|
| <b>General properties</b>               |                             |                      |                 |
| Density                                 | DIN EN ISO 1183-1           | g / cm <sup>3</sup>  | 1,31            |
| Water absorption                        | DIN EN ISO 62               | %                    | 0,2             |
| Flammability (Thickness 3 mm / 6 mm)    | UL 94                       |                      | V0 / V0         |
| <b>Mechanical properties</b>            |                             |                      |                 |
| Yield stress                            | DIN EN ISO 527              | MPa                  | 110             |
| Elongation at break                     | DIN EN ISO 527              | %                    | 15              |
| Tensile modulus of elasticity           | DIN EN ISO 527              | MPa                  | 4000            |
| Shore hardness                          | DIN EN ISO 868              | scale D              | 88              |
| <b>Thermal properties</b>               |                             |                      |                 |
| Melting temperature                     | ISO 11357-3                 | °C                   | 343             |
| Thermal conductivity                    | DIN 52612-1                 | W / (m * K)          | 0,25            |
| Thermal capacity                        | DIN 52612                   | kJ / (kg * K)        | 1,34            |
| Coefficient of linear thermal expansion | DIN 53752                   | 10 <sup>-6</sup> / K | 50              |
| Service temperature, long term          | Average                     | °C                   | -60 ... 250     |
| Service temperature, short term (max.)  | Average                     | °C                   | 310             |
| Heat deflection temperature             | DIN EN ISO 75, Verf. A, HDT | °C                   | 152             |

