

EK-SGC301PGF80

Polyetheretherketone (PEEK)

TECHNICAL DATA SHEET

Description

Sciengy® EK-SGC301PGF80 is a 30% CF&PTFE&graphite reinforced PEEK compound developed to provide excellent wear resistance, lower coefficient of friction and better chemical resistant.

CF+PTFE+Graphite, Low friction and wear

Series	Special Functional
ISO Designation	>PEEK+PTFE-(CF+G)30<
Process Method	Injection molding

Properties

Physical	Value	Units	Test Standard
Density	1.45	g/cm ³	ISO 1183
Mold Shrinkage (Machine Direction)	0.30	%	GB/T 15585
Mold Shrinkage (Transverse Direction)	0.90	%	GB/T 15585
Water Absorption (23°C-sat)	0.40	%	ISO 62
Flammability(1.6 mm)	V-0		IEC60695
Mechanical	Value	Units	Test Standard
Tensile Stress at Break (5 mm/min)	150	MPa	ISO 527
Tensile Modulus at Break (1 mm/min)	14	GPa	ISO 527
Elongation at Break (23°C)	2.2	%	ISO 527
Flexural Modulus at Break (23°C)	11.0	GPa	ISO 178
Flexural Strength at Break	230	MPa	ISO178
Charpy Impact Strength @23°C (V-notched)	8.0	kJ/m ²	ISO 179
Thermal	Value	Units	Test Standard
Melting Temperature (10°C/min)	343	°C	ISO 11357
Heat Deflection Temp. High Load (1.8 MPa)	315	°C	ISO 75
Glass Transition (Tg)	150	°C	ISO 11357
Thermal expansion coefficient (T<Tg) along flow	15	ppm/°C	ISO 11359
Thermal expansion coefficient (T>Tg) along flow	45	ppm/°C	ISO 11359
Thermal expansion coefficient (T<Tg) across flow	20	ppm/°C	ISO 11359

EK-SGC301PGF80
Polyetheretherketone (PEEK)

TECHNICAL DATA SHEET

Thermal expansion coefficient (T>Tg) across flow	115	ppm/°C	ISO 11359
Thermal conductivity (23°C)	0.8	W/mk	ISO 22007-4
Electrical Properties	Value	Units	Test Standard
Typical Processing Conditions	Value	Units	Test Standard
Drying Temp. / Time	150°C&3h or 120°C&5h(residual moisture<0.02%)		
Injection Molding Melt Temp.	170°C~200°C		
Temperature Settings	365/370/375/385/385°C(Nozzle)		
Hopper Temperature	Not greater than 100°C		
Gate	>2mm or 0.5*part thickness		