



VICTREX™ PEEK POLYMER 650P

General Information

Product Description

High performance thermoplastic material, unreinforced PolyEtherEtherKetone (PEEK), semi crystalline, coarse powder for extrusion compounding, low flow, colour natural.

Material Properties

Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3900	MPa	ISO 527-1
Tensile Stress (Yield, 23°C)	90.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	30	%	ISO 527-2
Flexural Modulus (23°C)	3600	MPa	ISO 178
Flexural Stress (23°C)	150	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	7.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength (23°C)	No Break		ISO 180
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature			ISO 11357-2
Onset	143	°C	
Midpoint	150	°C	
Melting Temperature	343	°C	ISO 11357-3
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (400°C)	500	Pa·s	ISO 11443

Typical Processing Information

Extrusion	Nominal Value	Unit
Drying Temperature	120 to 150	°C
Drying Time	3.0 to 5.0	hr
Melt Temperature	380 to 400	°C

Extrusion Notes

Important notes: