



VICTREX™ PEEK POLYMER 90GL60

General Information

Product Description

High performance thermoplastic material, 60% glass fibre reinforced PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection moulding, standard flow, colour natural/beige.

Applications where higher strength in a static system is required. Low coefficient of thermal expansion. Chemically resistant to aggressive environments, suitable for sterilization for medical and food contact applications.

Material Properties

Physical	Nominal Value	Unit	Test Method
Density (Crystalline)	1.83	g/cm ³	ISO 1183
Spiral Flow ¹	10.0	cm	Internal Method
Molding Shrinkage ²			ISO 294-4
Across Flow	0.60	%	
Flow	0.30	%	
Water Absorption (Saturation, 23°C)	0.40	%	ISO 62
Water Absorption Saturation (100°C)	0.55	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	25000	MPa	ISO 527-1
Tensile Stress			ISO 527-2
Break, 23°C	240	MPa	
Break, 125°C	150	MPa	
Break, 175°C	90.0	MPa	
Break, 275°C	50.0	MPa	
Tensile Strain (Break, 23°C)	1.5	%	ISO 527-2
Flexural Modulus (23°C)	23500	MPa	ISO 178
Flexural Stress (23°C)	360	MPa	ISO 178
Compressive Stress			ISO 604
23°C	230	MPa	
120°C	140	MPa	
200°C	65.0	MPa	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	11.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength (23°C)	50.0	kJ/m ²	ISO 180
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 23°C)	87.0		ISO 868

VICTREX™ PEEK POLYMER 90GL60

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	343	°C	ISO 75-2/Af
Glass Transition Temperature (Onset)	143	°C	ISO 11357-2
Melting Temperature	343	°C	ISO 11357-3
CLTE - Flow			ISO 11359-2
< 143°C	13	ppm/K	
> 143°C	15	ppm/K	
CLTE - Average			ISO 11359-2
< 143°C	30	ppm/K	
> 143°C	70	ppm/K	
Thermal Conductivity			ISO 22007-4
23°C ³	0.45	W/m/K	
23°C ⁴	0.55	W/m/K	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (23°C)	1.0E+16	ohms·cm	IEC 60093
Dielectric Strength (2.00 mm)	22.0	kV/mm	IEC 60243-1
Dielectric Constant (23°C, 1 kHz)	3.80		IEC 60250
Dissipation Factor (23°C, 1 MHz)	4.0E-3		IEC 60250
Comparative Tracking Index	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (2.0 mm)	960	°C	IEC 60695-2-12
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (400°C)	525	Pa·s	ISO 11443

Typical Processing Information

Injection	Nominal Value	Unit
Drying Temperature	120 to 150	°C
Drying Time	3.0 to 5.0	hr
Hopper Temperature	< 100	°C
Rear Temperature	360	°C
Middle Temperature	365 to 370	°C
Front Temperature	375	°C
Nozzle Temperature	380	°C
Mould Temperature	180 to 210	°C

Injection Notes

Runner: Die / nozzle >3mm, manifold >3.5mm

Gate: >2mm or 0.5 x part thickness

Notes

¹ Mould Temperature: 190°C, Melt Temperature: 380°C, 1.00 mm

² 380°C nozzle, 190°C tool

³ Average

⁴ Along flow