

Technical Data Sheet

Hostacom PPH MT20 FC BLK 73500



Polypropylene Compounds

Product Description

Hostacom PPH MT20 FC BLK 73500 is a 20% mineral filled PP homopolymer with medium melt flow rate.

Product is not yet UL certified.

This grade is not intended for medical, pharmaceutical, and drinking water applications.

Application	White Goods
Market	Electrical / Electronics
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7	g/10 min	ISO 1133-1
Melt Volume Flow Rate, (230 °C/2.16 kg)	9	cm ³ /10 min	ISO 1133-1
Density, (23 °C)	1.06	g/cm ³	ISO 1183-1/A
Mechanical			
Tensile Modulus, (23 °C)	2600	MPa	ISO 527-1, -2
Tensile Stress at Yield, (23 °C)	33	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Unnotched, (23 °C)	46	kJ/m ²	ISO 179-1/1eU
Thermal			
Vicat Softening Temperature, (A50)	152	°C	ISO 306