

## Technical Data Sheet

### Hostacom TRC 333N D62A30



Polypropylene Compounds

#### Product Description

Hostacom TRC 333N D62A30 is a 20% talc filled PP copolymer, with high flowability, high stiffness, high UV resistance, very good scratch resistance and low emissions. Product is available as a customized color matched, pellet form. This grade is delivered in D62A30 color version.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

|                          |                                                                  |
|--------------------------|------------------------------------------------------------------|
| <b>Application</b>       | Interior Trims                                                   |
| <b>Market</b>            | Automotive                                                       |
| <b>Processing Method</b> | Injection Molding                                                |
| <b>Attribute</b>         | Good UV Resistance; High Flow; High Stiffness; Scratch Resistant |

| Typical Properties                                        | Nominal Value | Units    | Test Method   |
|-----------------------------------------------------------|---------------|----------|---------------|
| <b>Physical</b>                                           |               |          |               |
| Melt Flow Rate, (230 °C/2.16 kg)                          | 17            | g/10 min | ISO 1133-1    |
| Density, (23 °C)                                          | 1.05          | g/cm³    | ISO 1183-1/A  |
| <b>Mechanical</b>                                         |               |          |               |
| Flexural Modulus, (23 °C, Tech. A)                        | 2000          | MPa      | ISO 178/A1    |
| Tensile Stress at Yield, (23 °C)                          | 21            | MPa      | ISO 527-1, -2 |
| Tensile Strain at Break, (23 °C)                          | 75            | %        | ISO 527-1, -2 |
| <b>Impact</b>                                             |               |          |               |
| Charpy Impact Strength - Notched                          |               |          |               |
| (23 °C)                                                   | 15            | kJ/m²    | ISO 179-1/1eA |
| (-30 °C)                                                  | 3             | kJ/m²    | ISO 179-1/1eA |
| <b>Thermal</b>                                            |               |          |               |
| Vicat Softening Temperature, (A50)                        | 130           | °C       | ISO 306       |
| Deflection Temperature Under Load, (0.45 MPa, Unannealed) | 95            | °C       | ISO 75B-1, -2 |