

## Technical Data Sheet

### Hostacom XBR 169 G G82299



Polypropylene Compounds

#### Product Description

Hostacom XBR 169 G G82299 is a 16% talc filled PP copolymer, with good processability, and surface appearance and scratch resistance and excellent impact/stiffness balance. Low density contributes to reduction of final part weight. The product is available as a customized color matched, pellet form. This grade is delivered in G82299 color version.

This product is also available in other colors, new colors can be developed depending on customer requirements.

*This grade is not intended for medical, pharmaceutical, food and drinking water applications.*

<b>Application</b>	Instrument Panels
<b>Market</b>	Automotive
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ISO 1133-1
Density, (23 °C)	1	g/cm <sup>3</sup>	ISO 1183-1/A
<b>Mechanical</b>			
Flexural Modulus, (23 °C, Tech. A)	1700	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	17	MPa	ISO 527-1, -2
<b>Impact</b>			
Notched Izod Impact Strength			
(23 °C)	25	kJ/m <sup>2</sup>	ISO 180/1A
(-40 °C)	4	kJ/m <sup>2</sup>	ISO 180/1A
<b>Thermal</b>			
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	100	°C	ISO 75B-1, -2