

Technical Data Sheet

Hostacom XBR 169G C7 C15974



Polypropylene Compounds

Product Description

Hostacom XBR 169G C7 C15974 is a 15% talc filled PP copolymer, with good processability, excellent impact resistance, excellent stiffness and excellent scratch resistance. Product is available as a customized color matched, pellet form.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Automotive Parts; Interior Trims
Market	Automotive
Attribute	Good Impact Resistance; Good Moldability; Scratch Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ISO 1133-1
Density, (23 °C)	1.01	g/cm³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	2000	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	20	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	20	kJ/m²	ISO 180