

Technical Data Sheet

Hifax EYC 361P G13063



Polypropylene Compounds

Product Description

Hifax EYC 361P G13063 is a 9% talc filled PP copolymer, with high melt flow rate and good impact resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G13063 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Exterior Trim
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance; High Flow

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	28	g/10 min	ISO 1133-1
Density, (23 °C)	0.95	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1250	MPa	ISO 178/A1
Tensile Strength, (23 °C)	19	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	50	kJ/m ²	ISO 180/1A
(-30 °C)	7	kJ/m ²	ISO 180/1A