



Hifax TRC 835X

Compounded Polyolefin

Product Description

Hifax TRC 835X high melt flow, medium high flexural modulus, mineral-filled, paintable thermoplastic elastomeric olefin (TEO) resin has a very good balance of properties. It was designed primarily for automotive exterior trim applications.

Product Characteristics

Test Method used	ISO
Processing Methods	Injection Molding
Features	Good Dimensional Stability, High Impact Resistance , Good Moldability
Typical Customer Applications	Exterior Applications

Typical Properties	Method	Value	Unit
Physical			
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	18	g/10 min
Density (23°C)	ISO 1183	1.04	g/cm ³
Mechanical			
Tensile Stress at Yield (23 °C)	ISO 527-1, -2	18	MPa
Flexural modulus (23 °C)	ISO 178	1700	MPa
Impact			
Multiaxial Impact Strength (23 °C, 2.2 m/s)	ASTM D3763	19	J
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	98	°C
Additional Information			
Mold shrinkage	ISO 294-4		