



Hostacom 62F4-2C

Compounded Polyolefin

Product Description

Hostacom 62F4-2C high melt flow, 1,900 MPa flexural modulus, precolored, 20% talc-filled polypropylene homopolymer has excellent heat aging characteristics, high chemical resistance and easy processability.

Product Characteristics

Test Method used	ASTM
Processing Methods	Injection Molding
Features	Good Chemical Resistance, Good Colorability, High Flow , Good Heat Aging Resistance , Homopolymer, Good Processability, Good Stiffness , Good Thermal Stability
Typical Customer Applications	Appliances, Automotive Parts, Hair Dryers, Shavers and Steam Irons, Housewares

Typical Properties	Method	Value	Unit
Physical			
Density -Specific Gravity	ASTM D 792	1.04	g/cm ³
Melt Flow Rate (230°C/2.16kg)	ASTM D 1238	20	g/10 min
Mechanical			
Flexural Modulus	ASTM D 790	1900	MPa
Tensile Strength @ Yield	ASTM D 638	31	MPa
Tensile Strength @ Break	ASTM D 638	26	MPa
Tensile Elongation @ Yield	ASTM D 638	5	%
Tensile Elongation @ Brk	ASTM D 638	20	%
Impact			
Notched Izod Impact (23 °C)	ASTM D 256	27	J/m
Hardness			
Rockwell Hardness (R-Scale)	ASTM D 785	98	
Thermal			
DTUL @66psi - Unannealed	ASTM D 648	116	°C
Additional Information			
Mold shrink, Linear-Flow	ASTM D 955	1.2	%