

Technical Data Sheet

Hostacom EKC 133N M61399



Polypropylene Compounds

Product Description

Hostacom EKC 133N M61399 is a 15% talc filled PP copolymer, with good impact/stiffness balance and good scratch resistance. The product is available in different color matched, pellet form. This grade is delivered in M61399 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	12	g/10 min	ISO 1133-1
Density, (23 °C)	1.02	g/cm ³	ISO 1183-1/A
Mechanical			
Flexural Modulus, (23 °C, Tech. A)	1850	MPa	ISO 178/A1
Tensile Stress at Yield, (23 °C)	21	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (-30 °C)	4	kJ/m ²	ISO 179-1/1eA
Thermal			
Vicat Softening Temperature, (A50)	132	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	56	°C	ISO 75B-1, -2