

Technical Data Sheet

Hostacom EP3307 T2 G76002



Polypropylene Compounds

Product Description

Hostacom EP3307 T2 G76002 is an unfilled polypropylene copolymer, with high impact resistance and good UV resistance. Product is available as a customized color matched, pellet form. This grade is delivered in G76002 color version.

This grade is not intended for medical, pharmaceutical, food and drinking water applications.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Flow; High Impact Resistance; UV Resistant

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ISO 1133-1
Density, (23 °C, Method A)	0.90	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus	1100	MPa	ISO 178
Tensile Stress at Yield	20	MPa	ISO 527-1, -2
Tensile Strain at Break	350	%	ISO 527-1, -2
Impact			
Notched Izod Impact Strength			
(23 °C)	45	kJ/m ²	ISO 180/1A
(-30 °C)	6	kJ/m ²	ISO 180/1A