

Technical Data Sheet

Hostacom ERC 213N NATURAL



Polypropylene Compounds

Product Description

Hostacom ERC 213N is a 15% talc filled PP copolymer, with good flow ability, excellent impact/stiffness balance and high scratch resistance. Product is available as a customized color matched, pellet form.

This grade is not intended for medical and pharmaceutical applications.

Application	Interior Trims
Market	Automotive
Processing Method	Injection Molding
Attribute	Good Impact Resistance

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	ISO 1133-1
Density, (23 °C)	1.01	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	1850	MPa	ISO 178
Tensile Strength, (23 °C)	21	MPa	ISO 527-1, -2
Impact			
Notched Izod Impact Strength, (23 °C)	35	kJ/m ²	ISO 180/1A