

(+) 18816996168

Poncioplastics.com

Technical Data Sheet

Polyfort APP30GM06NA-NA GAPEXNAT



Polypropylene, Homopolymer

Product Description

Gapex APP30GM06NA is a 30% Glass & Talc Filled, UV Stabilized, Impact-Modified Polypropylene

Attribute	Homopolymer
Forms	Pellets
Appearance	Natural Color
Filler/Reinforcement	Glass Fiber\Talc, 30%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	8.7	g/10 min	ASTM D1238
Mechanical			
Tensile Strength at Yield	44	MPa	ASTM D638
Flexural Modulus, (23 °C, Tangent)	3650	MPa	ASTM D790
Impact			
Notched Izod Impact	91	J/m	ASTM D256