

Technical Data Sheet

Polyfort FPP2B20CCBKBLK

Polypropylene, Homopolymer

Product Description

Polyfort FPP2B20CCBKBLK is a Polypropylene Homopolymer Glass Fiber, 20% filled material and is typically used in Injection Molding applications. Features include: Chemically Coupled, Good Impact Resistance, and Homopolymer.

Processing Method	Injection Molding
Attribute	Chemically Coupled; Good Impact Resistance; Homopolymer
Forms	Pellets
Filler/Reinforcement	Glass Fiber, 20%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate	3.5	g/10 min	ASTM D1238
Density - Specific Gravity	1.04	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield, (23 °C)	51.0	MPa	ASTM D638
Flexural Modulus, (Tangent)	2900	MPa	ASTM D790
Impact			
Gardner Impact	2.26	J	ASTM D3029
Notched Izod Impact, (23 °C, 3.18 mm)	64	J/m	ASTM D256
Hardness			
Durometer Hardness, (Shore D)	72		ASTM D2240
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	121	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	138	°C	ASTM D648

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	82 to 104	°C
Screw Speed	20 to 60	rpm
Processing (Melt) Temp	199 to 243	°C
Front Temperature	199 to 243	°C
Middle Temperature	199 to 243	°C
Rear Temperature	199 to 243	°C
Injection Rate	Moderate	
Back Pressure	<0.345	MPa
Mold Temperature	16 to 66	°C
Cushion	6.35 to 12.7	mm