

Technical Data Sheet

Polyfort NPP00GD01HB-BKBLK



Polypropylene, Unspecified (PP, Unspecified)

Product Description

Polyfort NPP00GD01HB-BKBLK is a Polypropylene, Unspecified Filler, 0.50% filled material and is typically used in Injection Molding applications. Features include: Impact Modified.

Processing Method	Injection Molding
Attribute	Impact Modified
Forms	Pellets
Appearance	Black
Additive	Impact Modifier
Application	Automotive Applications
Filler/Reinforcement	Filler, 0.50%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	7.5	g/10 min	ASTM D1238
Density - Specific Gravity	0.908	g/cm ³	ASTM D792
Mechanical			
Tensile Strength, (23 °C)	29.0	MPa	ASTM D638
Flexural Modulus			
(23 °C, 1% Secant)	1050	MPa	ASTM D790
(23 °C, Tangent)	1160	MPa	ASTM D790
Tensile Elongation at Break, (23 °C)	150	%	ASTM D638
Flexural Strength, (23 °C)	35.2	MPa	ASTM D790
Impact			
Gardner Impact, (23 °C)	32.2	J	ASTM D3029
Unnotched Izod Impact, (23 °C)	1300	J/m	ASTM D4812
Notched Izod Impact, (23 °C)	130	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	48.9	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	93.3	°C	ASTM D648

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 3.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	220 to 260	°C
Mold Temperature	30 to 60	°C