

Technical Data Sheet

Polyfort POLYPROPYLENE PP 1500X-01NAT



Polypropylene, Impact Copolymer

Product Description

PP 1500X is a specialty formulated high impact copolymer polypropylene.

Processing Method Injection Molding

Attribute High Impact Resistance; Impact Copolymer

Forms Pellets

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ASTM D1238
Density - Specific Gravity	0.9	g/cm ³	ASTM D792
Mechanical			
Tensile Elongation at Yield	>100	%	ASTM D638
Tensile Strength at Yield, (51 mm/min)	21.0	MPa	ASTM D638
Flexural Modulus	1000	MPa	ASTM D790
Impact			
Unnotched Izod Impact	No Break		ASTM D4812
Notched Izod Impact	530	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (66 psi)	85	°C	ASTM D648