

(+) 18816996168

Poncioplastics.com

Technical Data Sheet

Polyfort PPC-0220 GY7516GRY



Polypropylene, Unspecified (PP, Unspecified)

Product Description

Impact Modified PolypropyleneColors AvailableAdd "U" for UV StabilizedAdd "H" for Heat Stabilized

Processing Method Injection Molding

Attribute Impact Modified

Appearance Colors Available

Additive Impact Modifier

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ASTM D1238
Density - Specific Gravity	0.908	g/cm ³	ASTM D792
Mechanical			
Tensile Strength at Yield	33.2	MPa	ASTM D638
Flexural Modulus	1030	MPa	ASTM D790
Tensile Elongation at Break	>10	%	ASTM D638
Flexural Strength	37.9	MPa	ASTM D790
Impact			
Notched Izod Impact, (3.18 mm)	96	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	51.7	°C	ASTM D648

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 3.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	220 to 260	°C
Mold Temperature	30 to 60	°C