

## Technical Data Sheet

### *Pro-fax* RP223L



Polypropylene, Random Copolymer

#### Product Description

*Pro-fax* RP223L is a medium melt flow rate polypropylene random copolymer available in pellet form. This resin is typically used in cast and oriented film applications. In film applications it offers exceptional clarity, gloss, improved cold temperature impact resistance and lower and broader heat sealing properties as compared to conventional polypropylene homopolymer. *Pro-fax* RP223L is a barefoot resin with no slip, anti-block or other property specific additives. This product is manufactured with a non-phthalate catalyst system and is produced without animal derived components.

<b>Application</b>	Bags & Pouches; Breathable Film; Film Wrap; Food Packaging Film; Heavy Duty Packaging; Hygiene Film; Stationery Film; Twist Wrap Film
<b>Processing Method</b>	Cast Film; Oriented Film
<b>Attribute</b>	Good Heat Seal; Good Optical Properties; Good Processability; Medium Flow

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (230 °C/2.16 kg)	7.0	g/10 min	7.0	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm <sup>3</sup>	0.90	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	130000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			896	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	3800	psi			ASTM D638
(50 mm/min)			26.2	MPa	ASTM D638
Tensile Elongation at Yield	13	%	13	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength					
(73 °F, Method A)	0.95	ft-lb/in			ASTM D256
(23 °C, Method A)			51	J/m	ASTM D256
Gardner Impact, (23 °C, Geometry GC)	160	in-lbs	18	J	ASTM D5420
<b>Thermal</b>					
Deflection Temperature Under Load					
(66 psi, Unannealed)	174	°F			ASTM D648
(0.45 MPa, Unannealed)			79	°C	ASTM D648