

## **Technical Data Sheet**

## Purel/HP571R

Polypropylene, Homopolymer



## **Product Description**

*Purell* HP571R is a polypropylene homopolymer used for extrusion applications. It has a very narrow molecular weight distribution and is formulated with an anti-gasfading stabilisation package.

*Purell* HP571R is used for the production of continuous filaments. Typical applications are high-tenacity yarns (HTY) and spunbond nonwovens.

All potential activities for applications in the pharmaceutical, medical device, laboratory and diagnostics area have to be discussed with the relevant Technical and Business contacts first. To discuss a medical/pharmaceutical application please contact your local Lyondellbasell reference or your local Distributor.

Application Absorption & Filtration; Hygiene Nonwoven; Nonwovens; Wipes/Tissues

Market Textile

Processing Method Continuous Filament/Spinning; Fibers; Spunbond

Attribute Controlled Rheology; Extremely High Flow; Homopolymer; Narrow Molecular Weight

Distribution

	Nominal		
Typical Properties	Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	25	g/10 min	ISO 1133-1
Density	0.900	g/cm³	ISO 1183-1
Mechanical			
Flexural Modulus	1200	N/mm²	ISO 178
Tensile Stress at Break, (23 °C, 50 mm/min)	20	N/mm²	ISO 527-1, -2
Tensile Stress at Yield, (23 °C, 50 mm/min)	33	N/mm²	ISO 527-1, -2
Tensile Strain at Break, (23 °C, 50 mm/min)	650	%	ISO 527-1, -2
Tensile Strain at Yield, (23 °C, 50 mm/min)	11	%	ISO 527-1, -2
Thermal			
Vicat Softening Temperature, (A50)	151	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	74	°C	ISO 75B-1, -2