

Technical Data Sheet

XEP3758

Polypropylene, Impact Copolymer

Product Description

XEP3758 fully formulated impact polypropylene copolymer is available in pellet form. This resin is typically used in injection molding applications and offers excellent cold temperature impact resistance and stiffness/impact balance.

Regulatory Status

For regulatory compliance information, see XEP3758 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS). To obtain copies of these documents, please contact your LyondellBasell product safety representative.

Application	Caps & Closures; Containers; Crates
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	Contains High Antistat; Good Mold Release; Low Temperature Impact Resistance; Nucleated

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (230 °C/2.16 kg)	18	g/10 min	18	g/10 min	ASTM D1238
Density, (23 °C)	0.90	g/cm ³	0.90	g/cm ³	ASTM D792
Mechanical					
Flexural Modulus					
(0.05 in/min, 1% Secant, Procedure A)	170000	psi			ASTM D790
(1.3 mm/min, 1% Secant, Procedure A)			1170	MPa	ASTM D790
Tensile Strength at Yield					
(2 in/min)	3300	psi			ASTM D638
(50 mm/min)			23	MPa	ASTM D638
Tensile Elongation at Yield	5	%	5	%	ASTM D638
Impact					
Notched Izod Impact Strength					
(73 °F, Method A)	3.2	ft-lb/in			ASTM D256
(23 °C, Method A)			170	J/m	ASTM D256
Thermal					
Deflection Temperature Under Load					
(66 psi, Unannealed)	221	°F			ASTM D648
(0.45 MPa, Unannealed)			105	°C	ASTM D648