

## TECNOPRENE® DEV AK8LET1 NERO900 (PRELIMINARY)

Polypropylene, homopolymer, 40% glass fiber reinforced, chemically coupled, low emission, high heat stabilization.

### Typical mechanical properties

Tensile Modulus	9200 MPa	ISO 527-1/-2
Stress at break, 5mm/min	95 MPa	ISO 527-1/-2
Strain at break, 5mm/min	3.5 %	ISO 527-1/-2
Flexural Modulus	8900 MPa	ISO 178
Flexural Strength	160 MPa	ISO 178
Charpy impact strength, 23°C	60 kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, 23°C	12 kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	12 kJ/m <sup>2</sup>	ISO 180/1A

### Thermal properties

Temp. of deflection under load, 1.8 MPa	142 °C	ISO 75-1/-2
---	--------	-------------

### Flammability

Burning Behav. at 1.5mm nom. thickn.	HB class	UL 94
Burning Behav. at thickness h	HB class	UL 94

### Other properties

Density	1230 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Injection

Drying Temperature	80 - 100 °C
Drying Time, Dehumidified Dryer	2 - 3 h
Max. mould temperature	50 - 80 °C

### Processing Texts

Longer pre-drying times/storage      This product should be stored in a covered facility and kept away from moisture and heat.

---