

LAPRENE® 830...541

Typical mechanical properties

Stress at 100% elongation	0.52 MPa	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1.42 MPa	ISO 527-1/-2 or ISO 37
Stress at break	4.3 MPa	ISO 527-1/-2 or ISO 37
Elongation at break	790 %	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	29	ISO 48-4 / ISO 868
Tear strength, normal	17 kN/m	ISO 34-1

Other properties

Density	1120 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Max. mould temperature	20 - 40 °C
------------------------	------------

Processing Texts

Longer pre-drying times/storage	Must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	---