

LAPRENE® NATURALE 8K3000A60 - SEBS

Physical properties	Value	Unit	Test Standard
Density	1030	kg/m ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile stress at 100% strain	2.2	MPa	ISO 37
Tensile stress at 300% strain	4.3	MPa	ISO 37
Tensile strain at break (TPE)	612	%	ISO 37
Tensile stress at break (TPE)	11.3	MPa	ISO 37
Shore A hardness, 3s	64	-	ISO 868
Tear strength	37	kN/m	ISO 34-1

Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Zone1 temperature	175 - 185	°C	-
Zone2 temperature	185 - 195	°C	-
Zone3 temperature	195 - 205	°C	-
Nozzle temperature	185 - 195	°C	-
Extrusion Molding, Head Temperature	195 - 205	°C	Internal

Other text information

Pre-drying

2h@80C

Longer pre-drying times/storage

Laprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.