

(+) 18816996168

Poncioplastics.com



## SOFPRENE® 230NZ1335 NEUTRO - SEBS

| Physical properties | Value | Unit              | Test Standard |
|---------------------|-------|-------------------|---------------|
| Density             | 1000  | kg/m <sup>3</sup> | ISO 1183      |

| Mechanical properties (TPE)   | Value | Unit | Test Standard |
|-------------------------------|-------|------|---------------|
| Tensile strain at break (TPE) | 722   | %    | ISO 37        |
| Tensile stress at break (TPE) | 3     | MPa  | ISO 37        |
| Shore A hardness, 3s          | 36    | -    | ISO 868       |
| Tear strength                 | 16.6  | kN/m | ISO 34-1      |

### Typical injection moulding processing conditions

| Temperature       | Value     | Unit | Test Standard |
|-------------------|-----------|------|---------------|
| Zone1 temperature | 155 - 165 | °C   | -             |
| Zone2 temperature | 175 - 185 | °C   | -             |