

(+) 18816996168

Poncioplastics.com



SOFPRENE® 263BZA266 BIANCO - SEBS

Physical properties	Value	Unit	Test Standard
Density	900	kg/m ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile strain at break (TPE)	750	%	ISO 37
Tensile stress at break (TPE)	7	MPa	ISO 37
Shore A hardness, 3s	66	-	ISO 868
Tear strength	30	kN/m	ISO 34-1
Abrasion resistance	130	mm ³	ISO 4649

Electrical properties	Value	Unit	Test Standard
Surface resistivity	<1E11	Ohm	IEC 60093

Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Zone1 temperature	155 - 165	°C	-
Zone2 temperature	175 - 185	°C	-