

(+) 18816996168

Poncioplastics.com



SOFPUR® L NICOTINA 012NLN875 - SEBS

Physical properties	Value	Unit	Test Standard
Density	1100	kg/m ³	ISO 1183

Mechanical properties (TPE)	Value	Unit	Test Standard
Tensile strain at break (TPE)	600	%	ISO 37
Tensile stress at break (TPE)	10	MPa	ISO 37
Shore A hardness, 3s	70	-	ISO 868
Abrasion resistance	90	mm ³	ISO 4649

Typical injection moulding processing conditions

Temperature	Value	Unit	Test Standard
Zone1 temperature	165 - 175	°C	-
Zone2 temperature	175 - 185	°C	-