

FORPRENE® 65VS9ZA85

Typical mechanical properties

Stress at 100% elongation	682 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	870 psi	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	88	ISO 48-4 / ISO 868

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage	Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--