

FORPRENE® 6B0901A90

Typical mechanical properties

Stress at 100% elongation	856 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1060 psi	ISO 527-1/-2 or ISO 37
Shore A hardness, 15s	91	ISO 48-4 / ISO 868
Tensile set	31 %	ISO 2285

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Processing Texts

Longer pre-drying times/storage	Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--
