

FORPRENE® 6B0901D40

Rheological properties

Moulding shrinkage range, parallel	1.2 %	ISO 294-4, 2577
Moulding shrinkage range, normal	0.8 %	ISO 294-4, 2577

Typical mechanical properties

Stress at 100% elongation	1330 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1390 psi	ISO 527-1/-2 or ISO 37
Shore D hardness, 15s	41	ISO 48-4 / ISO 868

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Processing Texts

Longer pre-drying times/storage	Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--

Other Approvals

Other Approvals	<table><tr><th>OEM</th><th>Specification</th></tr><tr><td>Stellantis - PSA Group</td><td>B62 0020</td></tr><tr><td>Stellantis - PSA Group</td><td>B63 0020</td></tr></table>	OEM	Specification	Stellantis - PSA Group	B62 0020	Stellantis - PSA Group	B63 0020
OEM	Specification						
Stellantis - PSA Group	B62 0020						
Stellantis - PSA Group	B63 0020						