

FORPRENE® 6K5901A55

Typical mechanical properties

Stress at 100% elongation	276 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	450 psi	ISO 527-1/-2 or ISO 37
Shore A hardness, 3s	58	ISO 48-4 / ISO 868
Shore A hardness, 15s	56	ISO 48-4 / ISO 868

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage	Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--

Other Approvals

Other Approvals

OEM	Specification	Additional Information
VW Group	PV3930	
VW Group	PV3920	
VW Group	VW50123	DIN75201