

# FORPRENE® 6M0901A55

## Typical mechanical properties

|                           |         |                        |
|---------------------------|---------|------------------------|
| Stress at 100% elongation | 261 psi | ISO 527-1/-2 or ISO 37 |
| Stress at 300% elongation | 406 psi | ISO 527-1/-2 or ISO 37 |
| Shore A hardness, 15s     | 57      | ISO 48-4 / ISO 868     |

## Other properties

|         |          |          |
|---------|----------|----------|
| Density | 8 lb/gal | ISO 1183 |
|---------|----------|----------|

## Injection

|                        |             |
|------------------------|-------------|
| Max. mould temperature | 68 - 104 °F |
|------------------------|-------------|

## Processing Texts

|                                 |                                                                                                                                  |
|---------------------------------|----------------------------------------------------------------------------------------------------------------------------------|
| Longer pre-drying times/storage | Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat. |
|---------------------------------|----------------------------------------------------------------------------------------------------------------------------------|

---