

FORPRENE® 6MD5901D40

Typical mechanical properties

Stress at 100% elongation	1190 psi	ISO 527-1/-2 or ISO 37
Stress at 300% elongation	1290 psi	ISO 527-1/-2 or ISO 37
Shore D hardness, 15s	41	ISO 48-4 / ISO 868

Other properties

Density	8 lb/gal	ISO 1183
---------	----------	----------

Injection

Max. mould temperature	68 - 104 °F
------------------------	-------------

Processing Texts

Longer pre-drying times/storage	Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.
---------------------------------	--

Other Approvals

Other Approvals

OEM	Specification	Additional Information
Renault	EP04	PMR2020
Renault	EP04	Nero