

## FORPRENE® NERO 6NB901A90 - TPV

| Physical properties | Value | Unit              | Test Standard |
|---------------------|-------|-------------------|---------------|
| Density             | 958   | kg/m <sup>3</sup> | ISO 1183      |

| Mechanical properties (TPE)   | Value | Unit | Test Standard |
|-------------------------------|-------|------|---------------|
| Tensile stress at 100% strain | 6.9   | MPa  | ISO 37        |
| Tensile stress at 300% strain | 8.4   | MPa  | ISO 37        |
| Tensile strain at break (TPE) | 683   | %    | ISO 37        |
| Tensile stress at break (TPE) | 16.2  | MPa  | ISO 37        |
| Shore A hardness, 15s         | 95    | -    | ISO 868       |
| Shore D hardness, 15s         | 36    | -    | ISO 868       |
| Tear strength                 | 71    | kN/m | ISO 34-1      |

### Typical injection moulding processing conditions

| Temperature        | Value     | Unit | Test Standard |
|--------------------|-----------|------|---------------|
| Zone1 temperature  | 165 - 175 | °C   | -             |
| Zone2 temperature  | 175 - 185 | °C   | -             |
| Zone3 temperature  | 180 - 190 | °C   | -             |
| Nozzle temperature | 190 - 200 | °C   | -             |
| Mold temperature   | 180 - 190 | °C   | -             |

### Other text information

#### Pre-drying

3h@80C

#### Longer pre-drying times/storage

Forprene must be stored indoors in the original, unopened and undamaged packaging, away from direct sunlight, moisture and heat.