

GUR® 2024 - PE-UHMW

Description

Low entanglement, low bulk density UHMW-PE powder grade
Low entanglement, low bulk density UHMW-PE powder grade

Physical properties	Value	Unit	Test Standard
Elongational Stress F, 150/10	43.5	psi	ISO 21304-2
Average molecular weight	5.4E6	g/mol	Margolies' Equation
Density	58.1	lb/ft³	ISO 1183
MFR temperature	374	°F	ISO 1133
MFR load	47.6	lb	ISO 1133
Intrinsic viscosity	60900	in³/lb	ISO 1628-3
Viscosity number (PE and PP)	69200	in³/lb	ISO 1628-3
Average particle size, d50	250	µm	Laser scattering

Mechanical properties	Value	Unit	Test Standard
Charpy double 14° v-notch strength, 23°C	35.7	ft-lb/in²	ISO 21304-2
Wear by sandslurry method (based on GUR 4120=100)	100	-	Internal
Tensile modulus	120000	psi	ISO 527-2/1B
Tensile stress at yield	3190	psi	ISO 527-2/1B
Tensile strain at yield	13	%	ISO 527-2/1B
Tensile stress at 50% strain	3190	psi	ISO 527-2/1B
Tensile stress at break	5080	psi	ISO 527-2/1B
Tensile nominal strain at break	300	%	ISO 527-2/1B
Shore D hardness-TPE, 15s	60	-	ISO 868

Thermal properties	Value	Unit	Test Standard
Vicat softening temperature, 50°C/h 50N	176	°F	ISO 306

Electrical properties	Value	Unit	Test Standard
Volume resistivity, 23°C	>1E12	Ohm*m	IEC 62631-3-1
Surface resistivity, 23°C	>1E12	Ohm	IEC 62631-3-2

Characteristics

Special Characteristics	Heat resistant, Hydrolysis resistant, UV resistant
Product Categories	Low emission, Specialty, Unfilled
Processing	Injection molding
Delivery Form	Powder