

# GUR® 4014

HMW-PE powder grade for battery separators  
HMW-PE powder grade for battery separators

## Product information

|                            |               |                     |
|----------------------------|---------------|---------------------|
| Average molecular weight   | 1000000 g/mol | Margolies' equation |
| Average particle size, D50 | 115 µm        | laser scattering    |

## Rheological properties

|                                  |           |                     |
|----------------------------------|-----------|---------------------|
| Melt mass-flow rate, Temperature | 190 °C    |                     |
| Melt mass-flow rate, Load        | 21.6 kg   |                     |
| Viscosity number                 | 750 cm³/g | ISO 307, 1157, 1628 |
| Intrinsic viscosity              | 700       | ISO 307, 1157, 1628 |

## Typical mechanical properties

|                                             |           |                    |
|---------------------------------------------|-----------|--------------------|
| Tensile Modulus                             | 950 MPa   | ISO 527-1/-2       |
| Yield stress, 50mm/min                      | 24 MPa    | ISO 527-1/-2       |
| Yield strain, 50mm/min                      | 11 %      | ISO 527-1/-2       |
| Stress at 50% strain                        | 19 MPa    | ISO 527-1/-2       |
| Stress at break, 50mm/min                   | 41 MPa    | ISO 527-1/-2       |
| Nominal strain at break                     | 750 %     | ISO 527-1/-2       |
| Elongational stress, 150/10                 | 0.02 MPa  | ISO 21304-2        |
| Charpy double notched impact strength, 23°C | 125 kJ/m² | ISO 21304-2        |
| Shore D hardness, 15s                       | 61        | ISO 48-4 / ISO 868 |

## Tribological properties

|                                            |     |          |
|--------------------------------------------|-----|----------|
| Relative Wear                              | 170 | Internal |
| (based on GUR 4120=100), sandslurry method |     |          |

## Thermal properties

|                                          |       |             |
|------------------------------------------|-------|-------------|
| Temp. of deflection under load, 1.8 MPa  | 42 °C | ISO 75-1/-2 |
| Vicat softening temperature, 50°C/h, 50N | 80 °C | ISO 306     |

## Electrical properties

|                     |             |               |
|---------------------|-------------|---------------|
| Volume resistivity  | >1E12 Ohm.m | IEC 62631-3-1 |
| Surface resistivity | >1E12 Ohm   | IEC 62631-3-2 |

## Other properties

|              |           |          |
|--------------|-----------|----------|
| Density      | 940 kg/m³ | ISO 1183 |
| Bulk density | 450 kg/m³ | ISO 60   |


# GUR<sup>®</sup> 4014

## Characteristics

Food contact

FDA 21 CFR

## Stress-strain



# GUR® 4014

## Secant modulus-strain

