



**Product Data Sheet &
General Processing Conditions**

**PermaStat® 601 FR
Acrylonitrile Butadiene Styrene
(ABS)
Glass Fiber
Flame Retardant
ESD Protection
Permanently Anti-static**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	10 %	10 %	
Specific Gravity	1.34	1.34	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 - 0.0040 in/in	0.20 - 0.40 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	0.8 ft-lbs/in	43 J/m	D 256
unnotched 1/8 in (3.2 mm) section	5.0 ft-lbs/in	267 J/m	D 4812
Tensile Strength	6000 psi	41 MPa	D 638
Tensile Elongation	3.0 - 5.0 %	3.0 - 5.0 %	D 638
Tensile Modulus	0.45 x 10 ⁶ psi	3103 MPa	D 638
Flexural Strength	11000 psi	76 MPa	D 790
Flexural Modulus	0.45 x 10 ⁶ psi	3103 MPa	D 790

ELECTRICAL

Volume Resistivity	1E+09 - 9.9E+10 ohm.cm	1E+09 - 9.9E+10 ohm.cm	D 257
Surface Resistivity	1E+10 - 9.9E+11 ohm/sq	1E+10 - 9.9E+11 ohm/sq	D 257
Surface Resistance	1E+09 - 9.9E+10 ohm	1E+09 - 9.9E+10 ohm	ESD STM11.11
Static Decay			
MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 2.00 s	< 2.00 s	FTMS101C 4046.1

THERMAL

Ignition Resistance*			
Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	390 - 460 °F	199 - 238 °C
Mold Temperature	120 - 200 °F	49 - 93 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.10 %	0.10 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

(+) 18816996168
Poncioplastics.com

Do not exceed 520 °F (270 °C) melt temperature.
Desiccant Type Dryer Required.