

(+) 18816996168

Ponciplastics.com



Product Data Sheet & General Processing Conditions

RTP 603 FR A
Acrylonitrile Butadiene Styrene
(ABS)
Glass Fiber
Flame Retardant


PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.36	1.36	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0030 in/in	0.10 - 0.30 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	5.0 ft-lbs/in	267 J/m	D 4812
Tensile Strength	10500 psi	72 MPa	D 638
Tensile Elongation	2.0 %	2.0 %	D 638
Tensile Modulus	0.95 x 10 ⁶ psi	6550 MPa	D 638
Flexural Strength	15000 psi	103 MPa	D 790
Flexural Modulus	0.85 x 10 ⁶ psi	5861 MPa	D 790

THERMAL

Deflection Temperature			
@ 264 psi (1820 kPa)	220 °F	104 °C	D 648
@ 66 psi (455 kPa)	230 °F	110 °C	D 648
Ignition Resistance*			
Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	400 - 460 °F	204 - 238 °C
Mold Temperature	145 - 185 °F	63 - 85 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.10 %	0.10 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.