

(+) 18816996168

Poncioplastics.com



Product Data Sheet & General Processing Conditions

RTP 605 FR A
Acrylonitrile Butadiene Styrene
(ABS)
Glass Fiber
Flame Retardant


PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.44	1.44	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 in/in	0.10 %	D 955
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.2 ft-lbs/in	64 J/m	D 256
unnotched 1/8 in (3.2 mm) section	5.0 ft-lbs/in	267 J/m	D 4812
Tensile Strength	12000 psi	83 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	1.20 x 10 ⁶ psi	8274 MPa	D 638
Flexural Strength	18000 psi	124 MPa	D 790
Flexural Modulus	1.10 x 10 ⁶ psi	7584 MPa	D 790
THERMAL			
Ignition Resistance*			
Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	400 - 460 °F	204 - 238 °C
Mold Temperature	145 - 185 °F	63 - 85 °C
Drying	2 hrs @ 180 °F	2 hrs @ 82 °C
Moisture Content	0.10 %	0.10 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.