

(+) 18816996168

Ponciplastics.com



Product Data Sheet & General Processing Conditions

RTP 3485-3 Liquid Crystal Polymer (LCP) Carbon Fiber

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	30 %	30 %	
Specific Gravity	1.48	1.48	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0001 in/in	0.01 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.3 ft-lbs/in	69 J/m	D 256
unnotched 1/8 in (3.2 mm) section	7.0 ft-lbs/in	374 J/m	D 4812
Tensile Strength	22000 psi	152 MPa	D 638
Tensile Elongation	1.0 %	1.0 %	D 638
Tensile Modulus	5.00 x 10 ⁶ psi	34475 MPa	D 638
Flexural Strength	33500 psi	231 MPa	D 790
Flexural Modulus	3.50 x 10 ⁶ psi	24132 MPa	D 790

ELECTRICAL

Volume Resistivity	< 1E5 ohm.cm	< 1E5 ohm.cm	D 257
--------------------	--------------	--------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	545 °F	285 °C	D 648
Ignition Resistance*			
Flammability**	V-0 @ 1/8 in	V-0 @ 3.0 mm	D 3801

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	630 - 690 °F	332 - 366 °C
Mold Temperature	150 - 250 °F	66 - 121 °C
Drying	8 hrs @ 300 °F	8 hrs @ 149 °C
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

The key to successfully molding this material is to start mold open cycles as soon as the screw reaches its retracted position.