



**Product Data Sheet &
General Processing Conditions**

**RTP 207 G HS L
Nylon 4/6 (PA)
Glass Fiber
Heat Stabilized
Lubricated
Dry As Molded**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	40 %	40 %	
Specific Gravity	1.51	1.51	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0040 in/in	0.40 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.9 ft-lbs/in	101 J/m	D 256
unnotched 1/8 in (3.2 mm) section	20.0 ft-lbs/in	1068 J/m	D 4812
Tensile Strength	31000 psi	214 MPa	D 638
Tensile Elongation	3.0 %	3.0 %	D 638
Tensile Modulus	1.80 x 10 ⁶ psi	12411 MPa	D 638
Flexural Strength	47250 psi	326 MPa	D 790
Flexural Modulus	1.70 x 10 ⁶ psi	11722 MPa	D 790

ELECTRICAL

Volume Resistivity	> 1E12 ohm.cm	> 1E12 ohm.cm	D 257
--------------------	---------------	---------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	545 °F	285 °C	D 648
--	--------	--------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	560 - 620 °F	293 - 327 °C
Mold Temperature	175 - 300 °F	79 - 149 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.05 %	0.05 %
Dew Point	-40 °F	-40 °C

PROCESSING NOTES

Desiccant Type Dryer Required.