



**Product Data Sheet &
General Processing Conditions**

**RTP 211 G HS
Nylon 4/6 (PA)
Glass Fiber
Heat Stabilized
Dry As Molded**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	60 %	60 %	
Specific Gravity	1.75	1.75	D 792

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	2.5 ft-lbs/in	133 J/m	D 256
unnotched 1/8 in (3.2 mm) section	22.0 ft-lbs/in	1175 J/m	D 4812
Tensile Strength	36000 psi	248 MPa	D 638
Tensile Elongation	2.2 %	2.2 %	D 638
Tensile Modulus	3.00 x 10 ⁶ psi	20685 MPa	D 638
Flexural Strength	56800 psi	392 MPa	D 790
Flexural Modulus	2.80 x 10 ⁶ psi	19306 MPa	D 790

ELECTRICAL

Volume Resistivity	> 1E12 ohm.cm	> 1E12 ohm.cm	D 257
--------------------	---------------	---------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	545 °F	285 °C	D 648
--	--------	--------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	560 - 620 °F	293 - 327 °C
Mold Temperature	175 - 300 °F	79 - 149 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.05 %	0.05 %
Dew Point	-40 °F	-40 °C

PROCESSING NOTES

Desiccant Type Dryer Required.