



**Product Data Sheet &
General Processing Conditions**

**RTP 209 D
Nylon 6/12 (PA)
Glass Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	50 %	50 %	
Specific Gravity	1.51	1.51	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0010 - 0.0020 in/in	0.10 - 0.20 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	3.5 ft-lbs/in	187 J/m	D 256
unnotched 1/8 in (3.2 mm) section	25.0 ft-lbs/in	1335 J/m	D 4812
Tensile Strength	29000 psi	200 MPa	D 638
Tensile Elongation	2.0 - 4.0 %	2.0 - 4.0 %	D 638
Tensile Modulus	2.30 x 10 ⁶ psi	15858 MPa	D 638
Flexural Strength	45000 psi	310 MPa	D 790
Flexural Modulus	2.10 x 10 ⁶ psi	14480 MPa	D 790

THERMAL

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	480 - 545 °F	249 - 285 °C
Mold Temperature	140 - 200 °F	60 - 93 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.