



**Product Data Sheet &
General Processing Conditions**

**RTP 200 TC-C-25
Nylon 6/6 (PA)
Thermally Conductive
Electrically Conductive**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.68	1.68	D 792
MECHANICAL			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	5.0 ft-lbs/in	267 J/m	D 4812
Tensile Strength	17000 psi	117 MPa	D 638
Tensile Elongation	< 1.0 %	< 1.0 %	D 638
Tensile Modulus	4.40 x 10 ⁶ psi	30338 MPa	D 638
Flexural Strength	28000 psi	193 MPa	D 790
Flexural Modulus	3.50 x 10 ⁶ psi	24132 MPa	D 790
ELECTRICAL			
Volume Resistivity	< 1E2 ohm.cm	< 1E2 ohm.cm	D 257
Surface Resistivity	< 1E5 ohm/sq	< 1E5 ohm/sq	D 257
THERMAL			
Thermal Conductivity			
Through-plane	9.02 (BTU.in)/(hr.ft ² .°F)	1.30 W/(m.K)	E 1530
In-plane	27.78 (BTU.in)/(hr.ft ² .°F)	4.00 W/(m.K)	E 1461-92

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	150 - 225 °F	66 - 107 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.