

(+) 18816996168

Ponciplastics.com



Product Data Sheet & General Processing Conditions

RTP PA66 HI 25 GF BLK
Nylon 6/6 (PA)
Value Product
Glass Fiber
Impact Modified
Heat Stabilized

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	25 %	25 %	
Specific Gravity	1.27	1.27	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 - 0.0050 in/in	0.20 - 0.50 %	D 955

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	2.5 ft-lbs/in	133 J/m	D 256
unnotched 1/8 in (3.2 mm) section	15.0 ft-lbs/in	801 J/m	D 4812
Tensile Strength	14000 psi	97 MPa	D 638
Tensile Elongation	3.0 - 6.0 %	3.0 - 6.0 %	D 638
Tensile Modulus	1.00 x 10 ⁶ psi	6895 MPa	D 638
Flexural Strength	21000 psi	145 MPa	D 790
Flexural Modulus	0.90 x 10 ⁶ psi	6206 MPa	D 790

THERMAL

Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	530 - 570 °F	277 - 299 °C
Mold Temperature	150 - 225 °F	66 - 107 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.20 %	0.20 %
Dew Point	0 °F	-18 °C

PROCESSING NOTES

Desiccant Type Dryer Required.