

(+) 18816996168

Poncioplastics.com



**Product Data Sheet &
General Processing Conditions**

**RTP 1099 X 108836
Polybutylene Terephthalate (PBT)
High Gravity Compound**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	2.65	2.65	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0060 - 0.0090 in/in	0.60 - 0.90 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.5 ft-lbs/in	27 J/m	D 256
unnotched 1/8 in (3.2 mm) section	2.0 ft-lbs/in	107 J/m	D 4812
Tensile Strength	4500 psi	31 MPa	D 638
Tensile Elongation	< 1.0 %	< 1.0 %	D 638
Tensile Modulus	1.00 x 10 ⁶ psi	6895 MPa	D 638
Flexural Strength	7000 psi	48 MPa	D 790
Flexural Modulus	1.00 x 10 ⁶ psi	6895 MPa	D 790

THERMAL

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	460 - 520 °F	238 - 271 °C
Mold Temperature	175 - 225 °F	79 - 107 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.03 %	0.03 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.