



**Product Data Sheet &
General Processing Conditions**

**EMI 363
Polycarbonate (PC)
Stainless Steel Fiber
EMI/RFI Shielding
Electrically Conductive**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	20 %	20 %	
Specific Gravity	1.42	1.42	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0040 - 0.0050 in/in	0.40 - 0.50 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.3 ft-lbs/in	69 J/m	D 256
unnotched 1/8 in (3.2 mm) section	20.0 ft-lbs/in	1068 J/m	D 4812
Tensile Strength	10000 psi	69 MPa	D 638
Tensile Elongation	4.0 - 7.0 %	4.0 - 7.0 %	D 638
Tensile Modulus	0.42 x 10 ⁶ psi	2896 MPa	D 638
Flexural Strength	16800 psi	116 MPa	D 790
Flexural Modulus	0.49 x 10 ⁶ psi	3379 MPa	D 790

ELECTRICAL

Volume Resistivity	< 0 ohm.cm	< 0 ohm.cm	D 257
Surface Resistivity	< 1E4 ohm/sq	< 1E4 ohm/sq	D 257
Surface Resistance	< 1E3 ohm	< 1E3 ohm	ESD STM11.11
Static Decay MIL-PRF-81705D, 5kV to 50 V, 12% RH	< 0.50 s	< 0.50 s	FTMS101C 4046.1

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	271 °F	133 °C	D 648
Thermal Conductivity Through-plane	2.43 (BTU.in)/(hr.ft ² .°F)	0.35 W/(m.K)	E 1530

EMI

Shielding Effectiveness @ 2 mm thickness	83 dB @ 300 MHz	83 dB @ 300 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	87 dB @ 500 MHz	87 dB @ 500 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	91 dB @ 700 MHz	91 dB @ 700 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	95 dB @ 1000 MHz	95 dB @ 1000 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	96 dB @ 1300 MHz	96 dB @ 1300 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	99 dB @ 1500 MHz	99 dB @ 1500 MHz	D 4935

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	530 - 580 °F	277 - 304 °C

Mold Temperature	250 - 250 °F	71 - 121 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Use a reverse barrel profile. Remove hopper magnets. Allow 4 - 5 shots to properly disperse the conductive fibers. The surface finish should have a silver streaking appearance, not clumps.
Desiccant Type Dryer Required.