



**Product Data Sheet &
General Processing Conditions**

RTP 307 FR
Polycarbonate (PC)
Glass Fiber
Flame Retardant
Non-PBBO/E
UL94 V-0


The RTP series of flame retardant, glass fiber reinforced polycarbonate materials offer dimensional stability with improved heat distortion and ignition resistance performance over the base resin.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	40 %	40 %	
Specific Gravity	1.52	1.52	D 792
Molding Shrinkage			
1/8 in (3.2 mm) section	0.0005 - 0.0020 in/in	0.05 - 0.20 %	D 955
Water Absorption, 24 hrs @ 23°C	0.070 %	0.070 %	D 570

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	3.3 ft-lbs/in	176 J/m	D 256
unnotched 1/8 in (3.2 mm) section	17.0 ft-lbs/in	908 J/m	D 4812
Tensile Strength	21000 psi	145 MPa	D 638
Tensile Elongation	1.5 - 2.5 %	1.5 - 2.5 %	D 638
Tensile Modulus	1.70 x 10 ⁶ psi	11722 MPa	D 638
Flexural Strength	33000 psi	228 MPa	D 790
Flexural Modulus	1.50 x 10 ⁶ psi	10342 MPa	D 790
Hardness			
Rockwell, R	119	119	D 785

ELECTRICAL

Dielectric Strength, S/T, in oil	450 VPM	17.7 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	3.5	3.5	D 150
Dissipation Factor, 1 MHz, Dry	0.0060	0.0060	D 150
Volume Resistivity	> 1E16 ohm.cm	> 1E16 ohm.cm	D 257

THERMAL

Deflection Temperature			
@ 264 psi (1820 kPa)	300 °F	149 °C	D 648
@ 66 psi (455 kPa)	300 °F	149 °C	D 648
Ignition Resistance*			
Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	550 - 600 °F	288 - 316 °C

Mold Temperature	180 - 250 °F	82 - 121 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

PROCESSING NOTES

Desiccant Type Dryer Required.